

High Solid Productive 2K 2-1 Clearcoat CX 9850

2 Components high solid clearcoat based on new acrylic polyurethane copolymer resin technology, specially designed to crosslink at room temperature or under low-bake conditions. It is practically recommended for performance automotive coating and to be use in clear over base system.

PROPERTIES

- User friendly, very easy application with good flow properties.
- Excellent chemical and weather resistance.
- Excellent gloss retention and non-yellowing properties.
- Fast dry and good early hardness.
- Can be used for overall, panel, and spot repair.
- Has excellent buffability.

PRODUCTS

CX 9850	Corium HS Productive 2K 2-1 Clearcoat
CX 9851	Corium HS Productive 2K 2-1 Activator
CS 6000	Corium 2K Fast Thinner
CS 6600	Corium 2K Standard Thinner
CS 6900	Corium 2k Slow Thinner



CX 9850 TECHNICAL DATA SHEET

APPLICATION

Apply two coats directly over basecoat/colourcoat with 20-25 minutes flash time between coats. Upon completion, allowed 25 minutes flash before oven bake.



CX 9850
HS PRODUCTIVE 2K 2-1 CLEARCOAT

+



CX 9851
HS PRODUCTIVE 2K 2-1 CLEARCOAT

+



CS 6000 / CS 6600 / CS 6900

2

:

1

:

5-10%

MIXING RATIO

PRODUCT PREPARATION

MIXING RATIO

	FAST	STANDARD	SLOW
CX 9850	2	2	2
CX 9851	1	1	1
CS 6000	5-10%	-	-
CS 6600	-	5-10%	-
CS 6900	-	-	5-10%

2.5 HRS

POT OF LIFE AT 30°C

DIN 4: 16-18s
FORD 4: 16-18s
AFNOR 4: 18-20s

SPRAY VISCOSITY @30°C

20 - 25 mins
between COATS
25 mins
before BAKE

FLASH TIME

Dust Free 40 - 45 mins
Tack Free 2.5 - 3 hrs
Dry to Handle 5 hrs
Oven Bake 30 mins @ 60°C

DRYING TIME @30°C

SPRAY EQUIPMENT

FEED	FLUID TIP	SPRAY DISTANCE
Gravity	1.4-1.6mm	15-20mm
Suction	1.6-1.8mm	15-20mm
HVLP	1.3-1.5mm	10-15mm
Pressure	1.0-1.2mm	15-20mm

SPRAY PRESSURE

Gravity feed	: 1.8 - 2.5 bar
Suction feed	: 1.8 - 2.5 bar
HVLP	: 0.65 bar at nozzle
Pressure feed	: 1.8 - 2.5 bar

2

AMOUNT OF COATS

65-75 µm

DRY FILM THICKNESS

SAFETY INSTRUCTIONS

1. Keep container tightly closed in a well ventilated place. Keep away from sources of ignition - No Smoking.
2. Do not breathe vapour, avoid contact with skin and eyes.
3. During spraying, wear suitable air-fed respiratory equipment.